

**PRODUCT DATA SHEET****Appearance & Shape:** To be free from any defect such as flow, burrs, unevenness etc; as per IEC standards**Effective parameters irrespective of material grade (per piece)**

Parameter	Value	Unit
Effective Length (L_e)	60.1	mm
Effective Area (A_e)	55.9	mm ²
Effective Area (A_{Min})	55.9	mm ²
Effective Volume (V_e)	3360	mm ³
Approx. Weight (without gap)	17.0	g/piece

**T2610 Coated (Green)****Test Conditions:** 10kHz/150mV/CFR COIL,N=01/ L_0 =Zero/25°C


Material Grade	Initial Permeability (μ_{iac})	AL Value (nH)	D. Strength (kV)	Ordering code
CF195	5000 ±20%	5700 +30%/-20%	≥2.0	CF195 T2610 C
CF190	6000 ±20%	7000 +30%/-20%	≥2.0	CF190 T2610 C
CF197	7000 ±20%	8200 +30%/-20%	≥2.0	CF197 T2610 C
CF199	9000 ±20%	10500 +30%/-30%	≥2.0	CF199 T2610 C

Dimensions Un-Coated Core (in mm)

Dimension	Nominal	Maximum	Minimum
A	26.0	26.55	25.45
B	14.5	14.85	14.15
C	10.0	10.3	9.7

Dimensions Coated Core (in mm)

Dimension	Nominal	Maximum	Minimum
A	-	27.15	-
B	-	-	13.55
C	-	10.9	-



- Ferrite material for the product is in compliance with RoHS directive 2011/65/EU
- Epoxy Coating is UL Approved, UL file number E483791
- Coating material for the product is in compliance with RoHS directive 2011/65/EU

For general terms and conditions please visit

http://www.cosmoferrites.com/Downloads/Downloads/bcb70e7c-ae33-40ec-a881-0d5120db57b6_GTC.pdf**Regd. Office & Works: Jabli, Distt. Solan, Himachal Pradesh – 173 209 (India)****E-mail: sales@cosmoferrites.com**